

## **PRODUCT SHEET**

## **BRUSONI S1 SRC**

Prod. Ref.	78400-003		
Safety cat.	S1 P SRC		
Range of sizes	36 - 47 (3 - 12)		
Weight (sz. 8)	510 g		
Shape	А		
Width	11		

**Description:** Blue breathable textile and suede leather shoe, **SANY-DRY<sup>®</sup>** lining, antistatic, anti-shock, slipping resistant, non metallic **APT Plate** midsole **Zero Perforation** 

**Plus: COFRA SOFT** footbed, made of scented polyurethane, holed, antistatic, anatomic, soft and comfortable; the shape of the bottom part guarantees impact energy absorption; the upper part absorbs moisture and keeps the foot dry. Perfumed sole

Suggested uses: Warehouses, transportation sector, industries

**Care and maintenance:** Clean after each use and dry off away from direct heat. Avoid contact with aggressive chemicals or extreme temperature. Avoid immersion in sea water, lime water or cement mixed with water



0,19

≥ 0,13

## MATERIALS / ACCESSORIES

## SAFETY TECHNICAL SPECIFICATIONS

		Clause EN ISO 20345:2011	Description	Unit	Cofra result	Requirement
Complete shoe	Toe cap: ALUMINIUM made, ultra light, impact resistant until 200 J	5.3.2.3	Shock resistance (clearance after shock)	mm	15,5	≥ 14
	and compression resistant until 1500 kg	5.3.2.4	Compression resistance (clearance after compression)	mm	15	≥ 14
	Anti perforation midsole: in multi-layers highly tensile fabric, penetration resistant, Zero Perforation	6.2.1	Penetration resistance	N	To 1100 N	≥ 1100
					No perforation	
	Antistatic shoe: the bottom is fit for the dissipation of electrostatic charges	6.2.2.2	Electric resistance			
			- wet	MΩ	460	≥ 0.1
			- dry	MΩ	788	≤ 1000
	Energy absorption system	6.2.4	Shock absorption	J	27	≥ 20
Upper	Blue breathable textile	5.4.6	Water vapour permeability	mg/cmq h	> 2	≥ 0,8
			Permeability coefficient	mg/cmq	> 16,3	> 15
Upper	Blue suede leather	5.4.6	Water vapour permeability	mg/cmq h	> 4,7	≥ 0,8
	thickness 1,8/2,0 mm		Permeability coefficient	mg/cmq	> 46,9	> 15
Vamp	Textile, breathable, abrasion resistant, colour black	5.5.3	Water vapour permeability	mg/cmq h	> 6	≥ 2
lining	Thickness 1,2 mm		Permeability coefficient	mg/cmq	> 48	≥ 20
Quarter	SANY-DRY®, breathable, abrasion resistant, colour white	5.5.3	Water vapour permeability	mg/cmq h	> 9,8	≥ 2
lining	thickness 1,2 mm		Permeability coefficient	mg/cmq	> 78,5	≥ 20
Sole	Antistatic Polyurethane/TPU directly injected in the upper:	5.8.3	Abrasion resistance (lost volume)	mm <sup>3</sup>	35	≤ 150
	Outsole: Ice TPU, slipping resistant, abrasion resistant and hydrocarbons resistant.	5.8.4	Flexing resistance (cut increase)	mm	1	≤ 4
	Midsole: Blue polyurethane, low density, comfortable and anti-shock.	5.8.5	Interlayer bond strength	N/mm	> 5	≥ 4
		6.4.2	Hydrocarbons resistance ( $\Delta V$ = volume increase)	%	-0,8	≤ 2
	Adherence coefficient of the sole	5.3.5	SRA : ceramic + detergent solution - flat		0,60	≥ 0,32
			SRA : ceramic + detergent solution - heel (contact angle 7°)		0,51	≥ 0,28
			SRB : steel + glycerol – flat		0,27	≥ 0,18

SRB : steel + glycerol - heel (contact angle 7°)