

## TECHNICAL SHEET

# CHERSON - micro fleece sweatshirt

#### Description

- elasticated collar, waist and cuff,
- elongated back bottom to protect the back during bendings,
- neck zip



Maintenance

Maximum wash temperature: 30°C; Do not bleach; Do not dry in a tumble dryer; Do not dry clean; Do not iron.





Item

V553-0-03 Clay brown

Standards:



S – 4XL

Sizes

#### SAFETY TECHNICAL SPECIFICATIONS

	Test method	Description	Cofra result	Minimum requirement / range
Background fabric	EN ISO 1833-1977, SECTION 10	Composition:	100% polyester	
	EN ISO 12127:1996	Fabric mass per unit area	170 g/m <sup>2</sup>	
	EN ISO 13688:2013 5.3 (EN ISO 6630 / ISO 5077)	Dimensional change (3N/30°C)	warp: -0.4% weft: -0.3%	±3%
	ISO 105-C06	Colour fastness to Laundering at 40°C		1 - 5
		Colour change Staining:	4-5	
		diacetate	4	
		cotton	4-5	
		nylon	4	
		polyester	4-5	
		acrylic	4-5	
		wool	4-5	

Made by Workwear Technical Dept.

Version 1.0 date 23/09/2022 Drafts, rules, tables, data, directives and others informations here contained or attached to this document, are owned only by Cofra s.r.l. and must not be given or disclosed to any third party. It shall be prohibited to give, to share and to copy data contained in this notice and its relative attached documents by any subject different from the recipient according to both Article 616 of Penal Code and Personal Data Protection Code (Italian Legislative Degree n.196/2003). According to Article 98 and Article 99 of C.P.I, Cofra s.r.l will act through civil, administrative, or penal sanctions in respect of perpetrators in deference to articles 1 2 4 and successive ones of C.P.I. In case of dispute Italian exclusive jurisdiction will be apply as well as the competent court will be that one where Cofra s.r.l. has its registered office



### TECHNICAL SHEET

	ISO 105 E04	Colour fastness to perspiration	Acidic	Alkaline	
		Colour change	4-5	4-5	1 - 5
		Staining:			
		diacetate	4	4	
		cotton	4-5	4-5	
		nylon	4-5	4-5	
		polyester	4-5	4-5	
		acrylic	4-5	4-5	
		wool	4-5	4-5	
	ISO 105-B02	Colour fastness to light	5		1 - 5
	ISO 105-X12	Colour fastness to rubbing	Dry: 4 - 5		1 - 5
			Wet: 4 - 5		
	ISO 13938-2	Fabric: pneumatic method for determination of bursting strength and bursting distension	607 KPa		>100KPa
CHERSON	ISO 13938-2	Seam: pneumatic method for determination of bursting strength and bursting distension	576 KPa		>100KPa