





MOREIRAS – short							
<p>Description</p> <ul style="list-style-type: none"> • double back pocket , one closed with a flap, • elasticated waist, • fabric with high elastic perception, • flap-closed side pocket with a tool-pocket, • reflective insert, • wide front pockets 							
 <p>SLIM FIT</p>							
<p>Maintenance</p> <p>Maximum wash temperature: 40 °C; Do not bleach; Tumble drying possible drying at lower temperature; Drying in the shade; ironing at low temperature (max 110°C); Do not dry clean.</p> <div style="display: flex; justify-content: space-around; align-items: center;">       </div> <div style="text-align: center; margin-top: 10px;">  <p style="font-size: 8px; margin: 0;">WARNING: DO NOT IRON THE REFLEX INSERTS!</p> </div>	<table border="1" style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 20%;">Item</td> <td>V703-0-02 Navy/black V703-0-03 Clay brown/black V703-0-04 Anthracite/black V703-0-05 Black /black</td> </tr> <tr> <td>Standards:</td> <td>EN ISO 13688:2013/A1:2021 </td> </tr> <tr> <td>Sizes</td> <td>XS – 5XL</td> </tr> </table>	Item	V703-0-02 Navy/black V703-0-03 Clay brown/black V703-0-04 Anthracite/black V703-0-05 Black /black	Standards:	EN ISO 13688:2013/A1:2021 	Sizes	XS – 5XL
Item	V703-0-02 Navy/black V703-0-03 Clay brown/black V703-0-04 Anthracite/black V703-0-05 Black /black						
Standards:	EN ISO 13688:2013/A1:2021 						
Sizes	XS – 5XL						

SAFETY TECHNICAL SPECIFICATIONS

	Test method	Description	Cofra result	Minimum requirement / range
Background fabric	EN ISO 1833-1977, SECTION 10	Composition:	98% cotton 2% elastane	
	EN ISO 12127:1996	Fabric mass per unit area	250 g/m ²	
	EN ISO 13688:2013 4.2 (ISO 3071:2006)	The pH's determination from the watery extract	Oeko-Tex [®]	3,5 ≤ pH ≤ 9,5
	EN ISO 13688:2013 4.2 (EN 14362-1:2017)	Search of the aromatic and carcinogenic amines	Not recording Oeko-Tex [®]	≤30 ppm

	EN ISO 13688:2013 5.3 (EN ISO 6630 / ISO 5077)	Dimensional change (40°C)	warp: -1.4% weft: -3.0%	±3%
	ISO 105-C06	Colour fastness to Laundering at 40°C <i>Colour change</i> <i>Staining:</i> cotton polyester	4 4-5 4-5	1 - 5
	ISO 105 D01	Colour fastness to to dry cleaning <i>Colour change</i> <i>Staining:</i> cotton polyester	4-5 4-5 4-5	1 - 5
	ISO 105 E04	Colour fastness to perspiration <i>Colour change</i> <i>Staining:</i> cotton polyester	Acidic 4-5 4-5 4-5	Alkaline 4-5 4-5 4-5
	ISO 105-X12	Colour fastness to rubbing <i>Staining:</i>	Dry: 4-5	1 - 5
	EN ISO 105-X11	Colour fastness to hot pressing (110°C); <i>Colour change</i>	Dry: 4-5 Wet: 4-5	1 - 5
	ISO 105-B02	Colour fastness to light <i>Colour change</i>	5	1 - 5
	EN ISO 13934-1	Tensile strength	warp: 1000 N weft: 470 N	
	EN ISO 13937-2	Tear strength	Warp : 20 N Weft : 44 N	
	EN ISO 13937-1	Determination of tear force using ballistic pendulum method (Elmendorf)	warp: 23 N weft: 38 N	≥12 N
	ISO 12947-2	Determination of the abrasion resistance of fabrics by the Martindale	6000 cycles	
	ASTM D3107-07	Standard Test Methods for Stretch Properties of Fabrics Woven from Stretch Yarns Elongation (1,8 kgf / 30 min.) Recovery of elongation	20,4% 70.0%	
MOREIRAS	(EN ISO 13935-2)	Determination of maximum force to seam rupture using the grab method	Warp : 220 N Weft : 493 N	≥ 200 N