












VIDAGO – trousers

<p>Description</p>	<ul style="list-style-type: none"> • double back pocket , one closed with a flap, • elasticated waist, • fabric with high elastic perception, • flap-closed side pockets, one of which has a tool-pocket, • knee and leg ergonomic design, • reflective insert, • wide front pockets 		
<div style="display: flex; align-items: center;">  <div style="margin-left: 10px;"> <p>SLIM FIT Slim fit and tapered leg, without compromising comfort. With slim trousers, even the most demanding workers will be trendy during working hours.</p> </div> </div> <div style="display: flex; align-items: center; margin-top: 10px;">  </div>			
<p>Maintenance</p>	<p>Maximum wash temperature: 40 °C; Do not bleach; Tumble drying possible drying at lower temperature; Drying in the shade; ironing at low temperature (max 110°C); Do not dry clean.</p> <div style="display: flex; justify-content: space-around; align-items: center;">       </div> <div style="margin-top: 10px; background-color: yellow; padding: 5px; border: 1px solid black;">  <p>WARNING: DO NOT IRON THE REFLEX INSERTS!</p> </div>	<p>Item</p> <p>V702-0-02 Navy/black V702-0-03 Clay brown/black V702-0-04 Anthracite/black V702-0-05 Black /black</p> <p>Standards:</p> <p>EN ISO 13688:2013/A1:2021</p>  <p>Sizes</p> <p>XS – 5XL</p>	

SAFETY TECHNICAL SPECIFICATIONS

	Test method	Description	Cofra result	Minimum requirement / range
<p>Background fabric</p>	EN ISO 1833-1977, SECTION 10	Composition:	98% cotton 2% elastane	
	EN ISO 12127:1996	Fabric mass per unit area	250 g/m ²	
	EN ISO 13688:2013 4.2 (ISO 3071:2006)	The pH's determination from the watery extract	Oeko-Tex [®]	3,5 ≤pH≤ 9,5
	EN ISO 13688:2013 4.2 (EN 14362-1:2017)	Search of the aromatic and carcinogenic amines	Not recording Oeko-Tex [®]	≤30 ppm

	EN ISO 13688:2013 5.3 (EN ISO 6630 / ISO 5077)	Dimensional change (40°C)	warp: -1.4% weft: -3.0%	±3%
	ISO 105-C06	Colour fastness to Laundering at 40°C <i>Colour change</i> <i>Staining:</i> cotton polyester	4 4-5 4-5	1 - 5
	ISO 105 D01	Colour fastness to to dry cleaning <i>Colour change</i> <i>Staining:</i> cotton polyester	4-5 4-5 4-5	1 - 5
	ISO 105 E04	Colour fastness to perspiration <i>Colour change</i> <i>Staining:</i> cotton polyester	Acidic 4-5 4-5 4-5	Alkaline 4-5 4-5 4-5
	ISO 105-X12	Colour fastness to rubbing <i>Staining:</i>	Dry: 4-5	1 - 5
	EN ISO 105-X11	Colour fastness to hot pressing (110°C); <i>Colour change</i>	Dry: 4-5 Wet: 4-5	1 - 5
	ISO 105-B02	Colour fastness to light <i>Colour change</i>	5	1 - 5
	EN ISO 13934-1	Tensile strength	warp: 1000 N weft: 470 N	
	EN ISO 13937-2	Tear strength	Warp : 20 N Weft : 44 N	
	EN ISO 13937-1	Determination of tear force using ballistic pendulum method (Elmendorf)	warp: 23 N weft: 38 N	≥12 N
	ISO 12947-2	Determination of the abrasion resistance of fabrics by the Martindale	6000 cycles	
	ASTM D3107-07	Standard Test Methods for Stretch Properties of Fabrics Woven from Stretch Yarns Elongation (1,8 kgf / 30 min.) Recovery of elongation	20,4% 70.0%	
VIDAGO	(EN ISO 13935-2)	Determination of maximum force to seam rupture using the grab method	Warp : 220 N Weft : 493 N	≥ 200 N